


P-Plastic Primer

Field of application	Plastic parts.
Chemical bases	Special resin blend
General qualities	It is an one-component plastic primer that provides adhesion on plastic parts. When applying on PE and PE-PP mixed plastics, the surface must be passivated by applying heat treatment. It provides excellent adhesion to all other plastic surfaces. Ready to use. Never mixed with any other products.
Economy	Approx. 15 m ² /L/3-5 µm
Substrates	Plastic surfaces
Finishing materials	All Polaron Finishes.
Cleaning the equipment	Universal Acrylic Thinners and Cleaning Thinners
Colour	Metallic Grey
Storage life	Under normal storage conditions and unopened tins up to 2 years.

For professional use only. The technical information in this document has been carefully selected and prepared by us based on the current information. However, these data represent symbolic values. Since application variables are an important factor in product performance, this information should only be presented as a general guide. Polaron assumes no liability or responsibility for the use of this information. Due to any defect / error in this product, only the options of replacing the defective product or refunding the sales price are available, and the right to choose among them belongs to Polaron. See SDS for safety information.

P-Plastic Primer

APPLICATION DATA



Mixing ratio

1-component product

Ready for use

Never mixed with any other products



Application viscosity

18-20 sec. (DIN CUP 4 mm/20 °C)



Gravity feed

Spray nozzle (mm)

Pressure (bar)



Suction feed

1.3-1.5

3.0-3.5



HVLP/LVLP

1.3-1.5

see info

manufacturer



Spray coats/

1-2

Coat thickness

3-5 µm



Flash-off time

3-5 min. (till matting)



Drying

20 °C approx. 15-20 min.



Pot life

-



Safety

Use suitable respiratory protection (fresh air supply respirator is strongly recommended).

For more detailed information please see Safety Data Sheet.

For professional use only. The technical information in this document has been carefully selected and prepared by us based on the current information. However, these data represent symbolic values. Since application variables are an important factor in product performance, this information should only be presented as a general guide. Polaron assumes no liability or responsibility for the use of this information. Due to any defect / error in this product, only the options of replacing the defective product or refunding the sales price are available, and the right to choose among them belongs to Polaron. See SDS for safety information.